

KÖSTER KBE RS

Tehnički podaci / Artikel broj
Važi od 01. Juli 2008.

1.18

Visoko elastičan, bez rastvarača, brzo sazrevajući, rasprskavajući bitumenski premaz

Karakteristike

KÖSTER KBE RS je visoko elastičan, bez rastvarača hidroizolaciono jedinjenje na bitumenskoj bazi. Materijal je otporan na UV-zračenja i vremenske prilike. Posle aplikacije reaguje vrlo brzo i odmah je otporan na kišu. Posle 24 sata otporan je na vodu pod pritiskom.

Tehnički podaci

Viskoznost	
A-komponenta	400-800 mPa.s
B-komponenta	1-10 mPa.s
Gustina	
A-komponenta	1,05 g/cm ³
B-komponenta	1.01g/cm ³
Istezanje do pucanja	>1500%
Retrakcija	>80%
Temperatura aplikacije	+2°C do +35°C
Promenljivost organskog jedinjenja	>0,05% po težini

Polje aplikacije

KÖSTER KBE RS je otporan na pozitivan pritisak i koristi se u podrumima, tunelima i tankovima kao i za hidroizolaciju temelja, balkona i terasa.

Priprema podloge

Podloga mora da bude suva ili blago vlažna, nezaledjena, bez katrana, masnoća ili drugih nečistoća. Ukloniti sva ispušćena, ostatke maltera a polomljene rubove zaobliti. Uglove i prelaze popuniti i zao-bliti, šupljine popuniti KÖSTER Reparturnim malterom a spojeve popuniti odgovarajućim materijalom.

Aplikacija

KÖSTER KBE RS se rasprskava sa odgovarajućim dvokomponentnim rasprskavajućim uređajem (pumpom) koji omogućava dva odvojena mlaza koji se mešaju pri samoj aplikaciji. Materijal se ne aplikuje u nepovoljnim vremenskim uslovima

kao što su: vetar, kiša ili temperatura ispod 0°C. Materijal se mora zaštititi od mehaničkih oštećenja zasipanjem konstrukcije ili postavljanjem adekvatne zaštite (na pr: sitan pesak, razne folije..)

Potrošnja

Min. potrošnja 4kg/m² (približno debljini suvog sloja od 2,5mm). Na neravnim površinama potrošnja može biti značajno veća.

Čišćenje alata

Odmah po aplikaciji očistiti vodom. Suv materijal očistiti sa KÖSTER Bitumen Removerom.

Pakovanje

A-komponenta 1000l IBC kontejner
B-komponenta 100l bure

Skladištenje

Na hladnom i suvom, sa rokom upotrebe do 1. godine u originalnom pakovanju.

Korišćeni citati tehničkih listova:

- KÖSTER Bitumen Remover Art.- Nr. 9.03
- KÖSTER Repair Mortar Art.-Nr. 5.030

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.