

KÖSTER SALT STOP

Tehnički podaci / Artikal broj
Važi od 01. Januara 2007.

4.13

DEAKTIVATOR SOLI KOJE NEGATIVNO UTIČU NA ZIDOVE GRAĐEVINA

OPIS

Köster Salt Stop konvertuje oštećujuće sulfate i hloride u nerastvorne materije, čime se sprečava dalji negativan uticaj soli. Ne sadrži olovo i rastvarače, a svojim dejstvom podlogu čini čvršćom.

TEHNIČKI PODACI

- Materijal Hexafluorosilikat
- Viskoznost oko 10 mPa.s

OBLASTI PRIMENE

Kao dodatna mera pri restauraciji zidova sa restauracionim malterom, KD Sistemom. Takođe je pogodan za upotrebu na betonskim površinama, zidanim površinama, spojevima, cementnim i krečnim površinama, azbestno cementnim, i drugim površinama.

PODLOGA

Mineralna, čvrsta, suva, porozna i čista. Dobro ostrugati ostatke starog maltera, i produbiti spojeve nekoliko santimetara. Gipsane podloge nisu pogodne za ovaj sistem.

APLIKACIJA

PRIPREMA PODLOGE ZA KD-SISTEM

Materijal je gotov za primenu i na podlogu se može nanositi mazanjem ili prskanjem. Nanosi se u tri sloja i između slojeva se čeka od 6 – 18h. Raspored koncentracije po slojevima:

1. Sloj 1 deo Salt Stopa : 1 deo vode
2. Sloj 2 dela Salt Stopa : 1 deo vode
3. Sloj nerazblažen Salt Stop

Posle tri dana očetkati kristale soli sa podloge i tretirati podlogu KD-Sistemom.

PRIPREMA PODLOGE ZA RESTAURACIONI MALTER

Pre nanošenja špric maltera (Restoration Plaster Key, ili Restauracioni malter sa 20% SB Bondinga dodatog u odmerenu vodu), naneti jedan sloj nerazblaženog Salt Stopa. Aplikaciju špric maltera treba obaviti odmah ili najkasnije za tri sata. Posle minimum 24h restauracioni malter se može naneti u jednom ili više slojeva.

JAČANJE MINERALNIH PODLOGA, NPR. SPOJEVA, BETONA ITD.

Površina se prvo mehanički dobro očisti, pa se Salt Stop nanese po preporučenim koncentracijama:

1. Sloj 1 deo Salt Stopa : 1 deo vode
2. Sloj 2 dela Salt Stopa : 1 deo vode
3. Sloj nerazblažen Salt Stop

Sedimenti koji se na površini podloge mogu pojaviti po završenom sazrevanju, trebaju se ukloniti čišćenjem

POTROŠNJA

Oko 500 – 750 g/m²

ČIŠĆENJE ALATA

Odmah po upotrbi očistiti vodom

PAKOVANJE

12 kg kanistar.

SKLADIŠTENJE

Zaštićeno od mraza u zatvorenom kanistru oko 2 godine.
Pri radu koristiti zaštitnu opremu!

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.