

KÖSTER

Tehnički podaci / Artikal broj

5.030

Važi od 18.. December 2003

REPARATURNI MALTER

VODO-ODBOJNI, ZAVRŠNI MALTER ZA POPUNJVANJE I REPARACIJU

Opis

Reparaturni malter sa izuzetnim prijanjanjem čak i na površinu starih objekata.

Tehnički podaci

Drugi sloj se nanosi za otprilike 24 sata.
Specifična težina maltera 1.8kg/1

Polje primene

Reparaturni malter je pogodan za vodonepropusne reparacije. Uz to on se može koristiti za spravljanje vodonepropusnih gips smesa, sa kojima se izravnavaju hrapave površine ili spojevi, pre upotrebe tankih bitumenskih premaza, čak i pod vodom pod pritiskom. Pogodan je i kao malter za uzane prostore koji su predmet vode pod pritiskom, na spoju poda i zida, pre upotrebe bitumenskih premaza i mineralnih vodonepropusnih materijala (NB-, KD-sistemi.)

Podloga

Površina mora biti čista, zdrava, čvrsta, očišćena od ulja i masti, masnih boja i ostalih štetnih materija, koje mogu da spreče ili smanje prijanjanje. Prijanja na bilo koju čistu površinu.

Upotreba

30 kg reparaturnog maltera u 3-3.5 l vode + dodati 1 kg SB-vezujuće emulzije. Malter se mora ugraditi za maksimalno 3 sata. Koristiti obične alate za malterisanje.

Potrošnja

Oko 1,8kg/l zapremine, 18kg /m² /cm debljine.
Oko 2.5 kg/ dužnom metru holkera.

Čišćenje alata

Posle upotrebe isprati vodom,

Pakovanje

30 kg vreća

Skladištenje

Na suvom i u originalnom pakovanju preko 6 meseci.

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.