

KÖSTER LEVEL G

Tehnički podaci / Artikel broj
Važi od 01. Mart 2007.

5.08

SAMORAZLIVAJUĆA MINERALNA PODNA OBLOGA ZA VISOKA OPTEREĆENJA, ZA UNUTRAŠNJE I SPOLJNE POVRŠINE

OPIS

Jednokomponentna, samorazlivajuća visoko opteretiva struktura na bazi cementa sa izuzetnom sposobnošću vezivanja za mineralne podloge unutrašnjih i spoljašnjih površina. Koster NIVO G ima sposobnost brzog prijanjanja i spreman je za pešački saobraćaj već šposle 3 sata.

TEHNIČKI PODACI

Minimalna debljina sloja	8 mm
Maksimalna debljina sloja	20 mm
Radna temperatura sredine za ugradnju	+5°C – +30°C
Vreme ugradnje pripremljenog materijala	oko 15 min

POLJE PRIMENE

Za pokrivanje i izravnavanje unutrašnjih i spoljašnjih podnih površina. Pogodan kao industrijski pod u novim objektima i za reparaciju podnih površina. Takođe je pogodan i za sredine sa gustim saobraćajem gde u procesu smrzavanja i odleđivanja dolazi do oslobađanja agresivnih soli.

PRIPREMA PODLOGE

Beton mora da ima minimalnu čvrstoću na istezanje od 1,5 N/mm², i mora biti otprašen i očišćen od ulja, masti i ostalih štetnih komponenti koje mogu negativno da utiču na prijanjanje. Takođe, beton mora da bude zdrav, bez pukotina i šupljina. Vlažiti površinu 1 sat pre nanošenja Koster LEVEL G, izbegavajući stvaranje barica. Za vreme nanošenja sloja površina i dalje mora biti mokra. Nije potrebna upotreba prajmera.

PRIMENA

Izmešati 25 kg Koster LEVEL G sa 4 lit. Čiste pijaće vode u razlivajuću masu bez grudvica. Početi sa 3,5 lit. vode i dodavati zahtevanu količinu malo po malo mešajući stalno motornim mikserom koji ima max . 500 obrt./min. Na kraju dodati ostatak (0,5 lit.) vode da se postigne potrebna konzistencija za upotrebu. Pomenuta količina vode po džaku ne sme se prekoračiti. Zadnje 3 min. Mešati dvoosovinskim mikserom ili mikserom sa velikom oscilacijom. Izliti zamešan Koster LEVEL G na mokru površinu i razvući (rasplanirati) materijal na traženu visinu sa nazubljenom hoblom ili ravnjačom. Tako razvlačiti i ravnjati materijal do zahtevane debljine sloja. Nakon što odstoji minimum 3 sata sloj je spreman da primi pešački saobraćaj.

POTROŠNJA

Oko 1,7kg/m² za debljinu sloja od 1 mm

PAKOVANJE

Pakuje se u polietilen vreće od 25 kg.

ČUVANJE

Suvo u originalnim pakovanjima, kontejnerima.

ROK TRAJANJA

Šest meseci u neotvorenim vrećama.

MERE SIGURNOSTI

Pri radu koristiti zaštitnu opremu!

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.