

KÖSTER JOINT SEALANT FS-V

Tehnički podaci / Artikal broj
Važi od 01. Novembar 2007.

8.031

Tiksotropan, dvo-komponentni polusulfidni zaptivač spojeva-za vertikalne

OPIS

Köster-ov zaptivač spojeva FS-V je fleksibilan tiksotropan zaptivač na polisulfidnoj osnovi. On ostaje, jednom nanešen na suptrat, gumi sličan, fleksibilan zaptivač sa odličnom rezistencijom na mehaničke uticaje, uticaje slatke i morske vode, slanih rastvora, petrola i mineralnih ulja. Otporan je na truljenje, ne dozvoljava razvoj korenovog sistema biljaka i lako se oporavlja od deformacija.

TEHNIČKI PODACI

- Boja crna
- Odnos mešavine 100:13 wp (A:B)
- Vreme upotrebe oko 2h (+20°C, 50% rel.hum)
- Vreme sazrevanja oko 24h (+23°C, 4°F, 50% rel. vlage)
- Spec gustina oko 1,6 kg/l
- % oporavka deformiteta > 80 %
- % trajne deformacije 15 %
- Temperatura aplikacije +5°C- +40°C

POLJE APLIKACIJE

Zaptiva vertikalne spojeve ispod nivoa konstrukcija, pukotine u podrumima, temelje zgrada, spojeva kanalizacija, garaža, tunela i svuda gde se traži trajna elastičnost.

APLIKACIJA

Ivice spojeva moraju biti čiste, suve, čvrste, i slobodne od svih kontaminacija koje bi mogle negativno da utiču hidroizolacione osobine. Neophodno je podlogu prajmirati sa FS- prajmerom, i to apsorbentne površine sa dva sloja prajmera, a neapsorbentne površine jednim slojem prajmera. Obe komponente pažljivo sjediniti (najmanje 3 min.) sa nižom brzinom miksera. Popuniti spojeve prikladnim alatom, npr. glatkom mistrijom, oko 2h posle prajmera.

POTROŠNJA

| Širina spojeva u mm | 10 | 15 | 20 | 25 | 30 | 35 |
|-----------------------------------|------|--------------|--------------|--------------|--------------|--------------|
| Debljina spojeva u mm | 8 | 10 | 12 | 15 | 15 | 20 |
| Dozvoljena devijacija u mm | ± 2 | ± 2 | ± 2 | ± 3 | ± 3 | ± 4 |
| Rastojanje spojeva dozvoljena u m | do 2 | od 2 do 3 | od 3 do 5 | od 5 do 6 | od 6 do 7 | od 7 do 8 |
| Potrošnja kg/m | 0,13 | 0,24 | 0,38 | 0,60 | 0,72 | 1,12 |

ČIŠĆENJE ALATA

Odmah po upotrebi sa KB-POX Cleaner A.

PAKOVANJE

4kg kombi.set

SKLADIŠTENJE

Zastićeno od mraza i na suvom oko 6 meseci.

BEZBEDNOST

Pri rukovanju nositi zaštitnu opremu.

KORIŠĆEN TEHNIČKI PROSPEKT

KÖSTER FS-primer
KÖSTER KB-Pox Cleaner

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.